

PAT-NO: JP02002241962A
DOCUMENT-IDENTIFIER: JP 2002241962 A
TITLE: HOT DIP Zn-Al-Mg ALLOY PLATED STEEL SHEET AND
PRODUCTION METHOD THEREFOR
PUBN-DATE: August 28, 2002

INVENTOR-INFORMATION:

NAME	COUNTRY
TOKI, TAMOTSU	N/A
TAKEBAYASHI, HIROSHI	N/A
ISHIGAKI, HAJIME	N/A
TOMIYASU, TAKESHI	N/A
MATSUMOTO, MASAMITSU	N/A

ASSIGNEE-INFORMATION:

NAME	COUNTRY
SUMITOMO METAL IND LTD	N/A

APPL-NO: JP2001035686

APPL-DATE: February 13, 2001

INT-CL (IPC): C23C028/00, C22C018/00 , C22C018/04 , C23C002/06 ,
C23C002/26 , C23C002/40 , C23C022/26

ABSTRACT:

PROBLEM TO BE SOLVED: To provide a hot dip Zn-Al-Mg alloy plated steel sheet which has good workability, corrosion resistance and durability of adhesion, and a production method therefor.

SOLUTION: In the plated steel sheet, the surface of a hot dip plating film having a composition containing, 2.0 to 7.0% Al, 0.5 to 3.5% Mg and ≤ 0.5 g/m² Fe, and the balance Zn with inevitable impurities, and having a crystal structure in which the volume ratio of a Zn-Al-Mg ternary eutectic structure is $\geq 60\%$, further, a crystal structure in which the volume ratio of an Al-enriched layer is $\leq 10\%$ is provided with a chromate treated layer. Alternatively, the plated layer further contains one or more kinds of groups

selected from Ti, Nb, V and Sr by 0.001 to 0.05%. Alternatively, the content of hexavalent chromium in the chromate treated layer is ≤ 25 mg/m² expressed in terms of metallic chromium. On the production, when the plating bath does not contain Ti or the like, preferably, cooling is performed at a cooling rate of $\geq 15^{\circ}\text{C/sec}$ till the plating film is perfectly solidified after the plating.

COPYRIGHT: (C)2002,JPO